## **Product Specification Sheet**



## Dubl Kote® LSE - 1/8"

**Material Description:** DUBL KOTE® LSE consists of closed-cell foam coated on both sides with an extremely aggressive rubber-based adhesive, designed for quick initial bond to LSE plastics, such as polyethylene or polypropylene. Also has faster bond to UV coated board, UV cured inks, and powder coated metals. The foam carrier is flexible and conformable for filling spaces and joining irregular surfaces.

Product Information	Description	
Carrier	Crosslinked Polyethylene	
Adhesive	Rubber Based	
Release Liner	Silicone coated paper	
Application Temperature (°F)	65 to 100	
Service Temperature (°F)	-20 to 150	
Thickness (inch)	0.125	
Foam	Typical Properties	Test Method
Color:	White / Black	Visual
Density (lb/ft <sup>3</sup> ):	2.7 - 3.3	ASTM D3575
Tensile Strength (psi) MD:	126	ASTM D3575
Tensile Strength (psi) CD:	96	ASTM D3575
Elongation (% to break) MD:	232	ASTM D3575
Elongation (% to break) CD:	224	ASTM D3575
Compression Deflection @25% (psi):	7	ASTM D3575
Compression Set @50% compression:	20	ASTM D3575
A allo a si as	Terrical)/ales	Tast Mathemat
Adhesive	Typical Value	Test Method
180° Peel Adhesion (lb/in)	9.1 min	PSTC-101
Shear Adhesion (hours):	8	PSTC-107
1in², 10lb, 72°F		
Quick Stick (lb/in):	9.2 min	PSTC-5

\*Tests are performed on 2 mil PET

## Storage

Tape should be stored within its' original packaging, in a dry place at Room Temperature (72°F). If room temperature is not possible, the storage temperatures should not exceed 39°F to 100°F. When the tape is stored under these conditions, the shelf life would be 18 months from the date of shipment.

Duraco provides this information and recommendations for informative purposes only. The data is intended as a guide only and is presented without guarantees and without assumption of liabilities resultant from the use of information provided.

duraco.com