

# HIGH DENSITY URETHANE (PORON<sup>®</sup>)

#### Superb compression resistance

A open cell foam that exhibits closed cell characteristics when compressed. It offers very low compression set, good shock absorption, and low out-gassing. Available in rubber-based or acrylic-based.

### **FEATURES:**

- Very low compression set
- Good shock absorption
- Low out-gassing
- Ideal for open/close gasket applications

#### **APPLICATIONS:**

- Electrical enclosures
- Access doors/panels
- Louver and vent gasketing
- Lighting
- HVAC enclosures
- Electronics

#### **SPECIFICATIONS:**

- Test Method: ASTM D3574
- Density (lb/ft3): 15
- Compression Deflection: 4 to 8 psi
- Compression Set (50%): 10 max
- Service Temperature: Rubber-based: -20°F to 150°F;

Acrylic-based: -20°F to 190°F

• Flammability: FMVSS 302 UL94 HBF ≥ 3/16"

## Can't find your size? We customize.



#### **STANDARD ROLLS**

3" diameter core

Part Number	Thickness	Width	Length	Adhesive	Rolls/Carton
	in	in	ft		
472076	1/8	1/2	50	Acrylic	20
472078	1/8	1	50	Acrylic	10
472079	1/4	1/2	50	Acrylic	20
472081	1/4	1	50	Acrylic	10
472084	1/2	1	25	Acrylic	10
472085	1/8	1/2	50	Rubber	20
472087	1/8	1	50	Rubber	10
472088	1/4	1/2	50	Rubber	20
472089	1/4	3/4	50	Rubber	13
472090	1/4	1	50	Rubber	10
472091	1/2	1/2	25	Rubber	20
472093	1/2	1	25	Rubber	10

#### **NEED QUICK TURNAROUND?**



EXPERTS





SERVICE







CUSTOM CONVERTING

duraco.com

\*Roll diameter listed is nominal with a tolerance of +/- 6%.

